Weathershield[®]

Glossy

Weathershield[®] Glossy is a 3.2 mil (80μ) polymeric calendared PVC laminating film with a gloss finish, coated on one side with a pressure sensitive, solvent acrylic adhesive that is protected by a bleached Kraft release paper coated on one side with siliconised PE.

- SUITABLE FOR OUTDOOR APPLICATIONS, INCLUDING BANNERS, VEHICLE GRAPHICS (FLAT OR CURVED SURFACES) AND COMMERCIAL SIGNS, AS IT OFFERS SUPERB CLARITY FOR COLOR OPTIMISATION
- WHEN MATCHED WITH A HIGH QUALITY, POLYMERIC PRINT MEDIA, WEATHERSHIELD[®] GLOSSY OFFERS ITS BEST LONG-TERM PERFORMANCE

For more information, performance and warranty guidelines please contact your local Drytac office.

© 2022 Drytac Corporation. E&OE. All other trademarks are the property of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Film	Gloss Polymeric Calendared PVC	
Adhesive	Solvent Acrylic (Pressure Sensitive)	
Release Liner	1 Side PE Coated Siliconised Kraft Paper	
PRODUCT CHARACTERISTIC		
Film Weight	3.2 mil (80µ) ⁴ .1 mil	
Adhesive Layer	0.9 mil (22µ) (102µ)	
UV Protection Factor	Yes	
Outdoor Durability	7 years	
Fire Ratings	Class 0 (BS 476 Part 6 and 7) Class 1 or A (ASTM E 84; UL 723) PASS (CAN/ULC-S102)	
Service Temperature Range		
Service Temperature Range Peel Strength (20 min, FTM1)	PASS (CAN/ULC-S102) -4°F to 203°F	
	PASS (CAN/ULC-S102) -4°F to 203°F (-20°C to 95°C)	

PROCESS SETTINGS

quipment Type & Tempera	ture Speed	
Roller Laminator Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute	-
Press No	ot recommended	/
		DRYTAC
	A	DHESIVE SCIENC

Europe

Filwood Road, Fishponds, Bristol, BS16 3RY, United Kingdom bristol@drytac.com Tel: +44 (0) 117 958 6500

Canada

30 Driver Road, Brampton, Ontario, L6T 5V2, Canada toronto@drytac.com Tel: +1 800.353.2883

USA

5401-B Eubank Road, Sandston, Virginia, 23150, USA customerservice@drytac.com Tel: +1 800.280.6013

www.drytac.com