



MIDCOMP
CONSUMABLES

MC-PVC-BB-1370

PVC Frontlit Black Back-510g- 1370mmx50m

Item	Unit	Value	Test Method
Base Fabric	Denier (High tenacity yarn) 100%PES	1000DX1000D	DIN EN ISO2060
Construction	Weaving /inch	9x9	DIN60001
Weight of Fabric	Gsm/m2	85 ± 5	DIN53352 BS3424 Method5B
Weight of PVC	Gsm/m2	425 ± 5	DIN53352 BS3424 Method5B
Total Weight	Gsm/m2	510 ± 10	DIN53352 BS3424 Method5A
Thickness	mm	0.39 ± 0.02	DIN EN ISO 2286 - 3
Width	cm	Up to 510	0.9 ~ 3.2m
Breaking Strength	N/5cm	Warp	1350
		Weft	1200
Tearing Strength	N	Warp	245
		Weft	185
Adhesion	N/5cm	60	DIN53357 BS3425 Method9B
Temperature Resistance	°C	- 20 ~ 70	DIN53357 BS3425 Method10
Lacquering	NONE		
Flammability	Upon Client's request, we can reach: B1, B2, NFPA701, DIN75200 etc.		
Low Cadmium & Heavy Metals	Upon Client's request, we can reach: EN71-3		